

PRODUCT INFORMATION

KTT333

FACE STOCK:

	Representative Data	Test Method
Basis Weight (24x36-500 Sheets)	45# (73.2 g/m ²) Avg	TAPPI T-410
Caliper	3.4 Mils (86.3 Microns) Avg	TAPPI T-411
Brightness	92% Avg	TAPPI T-525
Smoothness	10,000 sec Avg	TAPPI T-479
Opacity	93% Avg	TAPPI T-425

APPLICATION NOTES:

KTT333 is a biaxially oriented, multilayer polypropylene featuring moisture resistance as well as strength and durability.

Kanzaki's new smudge resistant coating offers a superior thermal transfer printing surface. Testing has revealed characteristics that may enable end users to reduce printer energy, thereby lengthening printhead life.

KTT333 is compatible with flexographic printing and is ideal for industrial use, shelf marking, parts and inventory labels, and anywhere a strong, durable label stock is needed.

The data described in this product information sheet represent product averages and should be utilized only after allowing for accepted industry variances. Vendor shall not be responsible for liability resulting from any deviation from this information, and all products should be pretested to ensure that products meet all intended requirements of specific end-use application.